

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

All Purpose Matt Acrylic

SECTION A:	DESCRIPTION A good quality general purpose water-based matt acrylic paint for interior and exterior surfaces with excellent opacity, available in white and a range of colour card colours. Matt finish to hide imperfections and is non-yellowing. Formulated to meet the specification of S.A.B.S. 1586:2007 Grade 2.
SECTION B:	COMPOSITION Co-polymer emulsion
SECTION C:	PHYSICAL PROPERTIES Colour: White and as per colour card Appearance: Matt Gloss: <10% @ 85° Viscosity: 95 - 100 Ku @ 25°C S.G.: 1.25 - 1.51 (depending on colour) Mass Solids: 57 - 62% Volume Solids: 37 - 42% Shelf Life: 12 Months Storage Conditions: Normal Pack Size: 1ℓ, 5ℓ, 10ℓ, 20ℓ
SECTION D:	APPLICATION PROPERTIES Method: Brush, airless spray or roller Spreading Rate: 7 - 9m ² /l Number of coats: Two Drying Time @ 250 C: Hard 4hrs (depending on moisture and humidity). Allow 14 days to cure before washing. Overcoating Time @ 250 C: 4 hrs Thinning: Not Applicable Cleaning Solvent: Water Recommended systems: As described above Recommended DFT: 50 microns
SECTION E:	PRECAUTION Flash point: Water-based Toxicity: See M.S.D.S.
SECTION F:	SURFACE PREPARATION - All surfaces must be thoroughly clean, dry, free from grease, dirt or old flaking paint. - All loosely adhering material and powder, i.e. Distemper or Lime, must be removed and a coat of Excelsior SURFCON (Surface Conditioner) be applied and allow ± 18 hours to dry. NEW WOODWORK - Rub down with fine sandpaper and seal knots. - Prime with Excelsior WOOD PRIMER. - Follow with one coat Excelsior UNIVERSAL UNDERCOAT. NEW METAL SURFACES - Metal surfaces must be primed with the appropriate primer! A. NEW GALVANISED IRON - Remove storage oil with GALVANISED IRON CLEANER and prime with one coat of Excelsior AQUA-METALPRIME ANTI-CORROSIVE PRIMER.



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

All Purpose Matt Acrylic.../continued

B. NEW MILD STEEL

- Prime with H2O PRIMER RED OXIDE etching water-based primer. (New formulation) or AQUA METALPRIME ANTI-CORROSIVE PRIMER.
- or Alkyd based GP RED OXIDE PRIMER
- or Excelsior ZP PRIMER (with anti-corrosive Zincphosphate pigments).

NEW PLASTER

Once plaster is completely dry. Apply one coat of either:

- Excelsior AQUA-PLASTER PRIMER (Water-based).
- or Excelsior PLIOLITE PLASTER PRIMER (Goodyear France technology) (Solvent-based).
- or Excelsior ALKALI RESISTANT PLASTER PRIMER (Solvent-based).

PREVIOUSLY PAINTED EMULSION (PVA/Acrylic) SURFACES

- Remove dirt and grime with SUGAR SOAP.
- Loose material must be removed with sandpaper.
- Seal powdery surfaces with Excelsior SURFCON (Surface Conditioner).

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

- Sandpaper thoroughly.
- Apply one coat of Excelsior UNIVERSAL UNDERCOAT and allow \pm 18 hours to dry.

SECTION G:

NOTE

No guarantees are implied by the recommendations contained herein; since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.