

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

All Purpose Sheen Acrylic

- SECTION A: DESCRIPTION**
A good quality general purpose non yellowing waterbased sheen acrylic paint for interior and exterior surfaces. Excellent opacity and stain resistance with good scrubbability available in a white and a range of colour card colours. Formulated to meet requirements of SABS 1586 GRADE 2.
- SECTION B: COMPOSITION**
Co-polymer emulsion based.
- SECTION C: PHYSICAL PROPERTIES**
- | | |
|---------------------|------------------------------|
| Colour: | White and as per colour card |
| Appearance: | Sheen |
| Gloss: | 35 - 45% @ 85° |
| Viscosity: | 95 - 100 Ku @ 25°C |
| S.G.: | 1.20 - 1.25 |
| Mass Solids: | 38 - 43% |
| Volume solids: | 24 - 29% |
| Shelf Life: | 12 Months |
| Storage Conditions: | Normal |
| Pack Size: | 1l, 5l, 20l |
- SECTION D: APPLICATION PROPERTIES**
- | | |
|--------------------------|---------------------------------------------------------------------------------------|
| Method: | Brush, airless spray or roller |
| Recommended WFT: | 100um per coat |
| Spreading Rate: | 8 - 10m ² /l |
| Number of coats: | Two |
| Drying Time @ 25°C: | Hard 4hrs (depending on moisture and humidity). Allow 14 days to cure before washing. |
| Overcoating Time @ 25°C: | 4hrs |
| Cleaning Solvent: | Water |
| Recommended systems: | As described above |
- SECTION E: PRECAUTION**
- | | |
|--------------|--------------|
| Flash point: | Water-based |
| Toxicity: | See M.S.D.S. |
- SECTION F: SURFACE PREPARATION**
- All surfaces must be thoroughly clean, dry, free from grease, dirt or old flaking paint.
 - All loosely adhering material and powder, i.e. Distemper or Lime, must be removed and a coat of Excelsior BONDING LIQUID or SURFCON be applied and allow ± 18 hours to dry.
- NEW WOODWORK**
- Rub down with fine sandpaper and seal knots.
 - Prime with Excelsior WOOD PRIMER.
 - Follow with one coat Excelsior UNIVERSAL UNDERCOAT.
- NEW METAL SURFACES**
- Metal surfaces must be primed with the appropriate primer!
- A. NEW GALVANISED IRON**
- Remove storage oil with GI Cleaner and prime with one coat of



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

All Purpose Sheen Acrylic.../continued

- Excelsior AQUA-METALPRIME anti-corrosive primer.

B. NEW MILD STEEL

- Prime with H2O PRIMER RED OXIDE etching water-based primer. (New formulation).
- or Alkyd based GP RED OXIDE PRIMER
- or Excelsior ZP PRIMER (with anti-corrosive Zincphosphate pigments).

NEW PLASTER

Once plaster is completely dry. Apply one coat of either:

- Excelsior AQUA-PLASTER PRIMER (Water-based).
- or Excelsior PLIOLITE PLASTER PRIMER (Goodyear France technology) (Solvent-based).
- or Excelsior ALKALI RESISTANT PLASTER PRIMER (Solvent-based).

PREVIOUSLY PAINTED EMULSION (PVA/Acrylic) SURFACES

- Remove dirt and grime with SUGAR SOAP.
- Loose material must be removed with sandpaper.
- Seal powdery surfaces with Excelsior BONDING LIQUID or SURFCON.

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

- Sandpaper thoroughly.
- Apply one coat of Excelsior UNIVERSAL UNDERCOAT and allow \pm 18 hours to dry.

SECTION G:

NOTE

No guarantees are implied by the recommendations contained herein; since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.