

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

Chassis Black

SECTION A:	DESCRIPTION A slow drying, very flexible bitumen based product that can be used on most clean steel chassis surfaces. Most often applied to the underside of truck chassis as a rust and abrasion preventative.
SECTION B:	COMPOSITION Bitumen solution in white spirit with hydrocarbon resin
SECTION C:	PHYSICAL PROPERTIES Colour: Black Appearance: Semi-gloss finish Viscosity: 100 - 180" FC4 @ 25°C S.G.: 0.89 - 0.94 Mass Solids: 48 - 53% Volume Solids: 40 - 45% Shelf Live: 12 Months Storage Conditions: Normal / out of direct sunlight below 30°C. Pack Size: 1l, 5l, 20l
SECTION D:	APPLICATION PROPERTIES Method: Brush Roller or Spray Recommende Average Dft: 35 - 45 microns Spreading Rate: Variable due to application method Wet Film Thickness: 80 - 100 microns Recommended No of coats: 2 Drying Time: Surface 60mins, hard 16hrs max (depends on film thickness and temperature) Overcoating Time: Minimum 16hrs Thinning: Turpentine (white spirits) Cleaning Solvent: As above
SECTION E:	PRECAUTION Flash point: 17°C. Toxicity: See M.S.D.S. Store: Below 23°C
SECTION F:	SURFACE PREPARATION Contact Mylaw Technical Advisory service 011 474 1900
SECTION G:	NOTE No guarantees are implied by the recommendations contained herein since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.