

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™



Easi-Off

- SECTION A: DESCRIPTION:**
A fast acting paint stripper to remove decorative and many industrial paints. It may be applied to previously painted or varnished metal, wood or plaster surfaces, excludes plastic. It is water rinsable to flush off old paint.
- SECTION B: COMPOSITION**
Methylene chloride, wax , solvent blend
- SECTION C: PHYSICAL PROPERTIES**
- | | |
|---------------------|------------------------------------------------------------------------------------------------------------------------------------------|
| Colour: | Hazy viscous liquid |
| Appearance: | Gel-like |
| S.G.: | 1.08 - 1.13 |
| Mass Solids: | 13 - 18% |
| Volume Solids: | 4 - 9% |
| Shelf Live: | 12 Months |
| Storage Conditions: | Extreme caution is required for storage. Store out of direct sunlight and below 30°C. High temperatures can cause the packaging to burst |
| Pack Size: | 1ℓ, 5ℓ |
- SECTION D: APPLICATION PROPERTIES**
- | | |
|--------------------------|---------------------------------------------------------------------------------------------------------|
| Method: | Brush |
| Spreading Rate: | 6m ² /l (depending on surface porosity) |
| Wet Film Thickness: | Apply as required |
| Recommended No of coats: | 1 - 2 or as required |
| Drying Time: | N/A |
| Overcoating Time: | Allow as much time as possible after stripping a surface to ensure there is no residue of paintstripper |
| Cleaning Solvent: | Rinse old paint away with water |
- SECTION E: PRECAUTION**
Users should use safety glove and goggles to avoid contact with skin or eyes. In the case of accidental contact rinse thoroughly with large amounts of water and contact a physician. If taken internally contact a physician immediately.
- Take extreme care to store away from direct sunlight and high temperatures. Open containers ensuring the opening of the container is pointed away from eyes or skin as pressure caused by high temperatures can cause the containers to burst
- | | |
|--------------|------------------------------------------|
| Flash point: | Below 24°C |
| Toxicity: | Toxic. Store away from children and heat |
- SECTION F: PROCESS DETAILS**
Apply a liberal coat and leave for approx 15 minutes or until the paint film begins to wrinkle. Scrape off the softened paint with a paint scraper or putty knife. Repeat the procedure until all the paint is removed. Dispose of the waste carefully following local regulations. Rinse or hose the area with water. Allow the surface to dry and give the surface a final wipe clean with a cloth soaked in MINERAL TURPENTINE.
- SECTION G: NOTE**
No guarantees are implied by the recommendations contained herein ;since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.