

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™



Gold Paint

General Purpose

- SECTION A: DESCRIPTION**
This product imparts a deep gold finish to a wide variety of properly prepared surfaces (i.e. wood, steel, plaster etc). It is fast drying and easy to use. Ideal for small projects. It is recommended for interior use as the exterior durability is limited.
- SECTION B: COMPOSITION**
Rich gold powder in oil-based resin.
- SECTION C: PHYSICAL PROPERTIES**
- | | |
|---------------------|----------------------|
| Colour: | Gold |
| Appearance: | Semi-gloss finish |
| Viscosity: | 60 - 75" FC4 @ 25°C. |
| S.G.: | 0.93 - 0.97 |
| Mass Solids: | 40 - 45% |
| Volume Solids: | 33 - 38% |
| Shelf Live: | 12 Months |
| Storage Conditions: | Normal |
| Pack Size: | 500ml, 1L, 5L |
- SECTION D: APPLICATION PROPERTIES**
- | | |
|--------------------------|---|
| Method: | Brush |
| Recommended Average Dft: | 40 - 50 microns |
| Spreading Rate: | 12m ² /l |
| Wet Film Thickness: | ± 80 microns |
| Recommended No of coats: | 1 or 2 as required |
| Drying Time: | Surface 30 - 60mins, hard 18hrs max |
| Overcoating Time: | Minimum of 18hrs |
| Thinning: | Excelsior mineral turpentine |
| Cleaning Solvent: | Excelsior mineral turpentine |
| Recommended systems: | As a decorative finish for a wide variety of properly prepared surfaces |
- SECTION E: PRECAUTION**
REFER TO MATERIAL SAFETY DATA SHEETS(M.S.D.S.)
- | | |
|--------------|--------------|
| Flash point: | 13°C. |
| Toxicity: | See M.S.D.S. |
- SECTION F: SURFACE PREPARATION**
- All surfaces must be thoroughly clean, dry, free from grease, dirt or old flaking paint.
 - All loosely adhering material and powder, i.e. Distemper or Lime, must be removed and a coat of
 - Excelsior SURFCON (Surface Conditioner) be applied and allow ± 18 hours to dry.
- NEW WOODWORK**
- Rub down with fine sandpaper and seal knots.
 - Prime with Excelsior WOOD PRIMER.
 - Follow with one coat Excelsior UNIVERSAL UNDERCOAT.
- NEW METAL SURFACES**
- Metal surfaces must be primed with the appropriate primer!
- A. NEW GALVANISED IRON**
- Remove storage oil with Excelsior GALVANISED IRON CLEANER and prime with one coat of Excelsior AQUA-METALPRIME anti-corrosive primer.



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

Gold Paint.../continued

B. NEW MILD STEEL

- Prime with H2O PRIMER RED OXIDE etching water-based primer. (New formulation) or AQUA-METALPRIME anti-corrosive primer.
- or Alkyd based GP RED OXIDE PRIMER or Excelsior ZP PRIMER (with anti-corrosive Zincphosphate pigments).

NEW PLASTER

- Once plaster is completely dry. Apply one coat of either:
- Alkyd Excelsior PLASTER PRIMER (low alkalinity) recommended for interior plaster.
- or PLIOLITE PLASTER PRIMER (Goodyear France technology) for maximum priming benefits (high alkalinity) recommended for exterior plaster.

PREVIOUSLY PAINTED EMULSION (PVA/Acrylic) SURFACES

- Remove dirt and grime with SUGAR SOAP.
- Loose material must be removed with sandpaper.
- Seal powdery surfaces with Excelsior SURFCON (Surface Conditioner).

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

Sandpaper thoroughly.

Apply one coat of Excelsior UNIVERSAL UNDERCOAT and allow ± 18 hours to dry.

SECTION G:

NOTE

No guarantees are implied by the recommendations contained herein ;since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.