

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™



Wise Buy Hi-Gloss Enamel

SECTION A:	DESCRIPTION A low cost high-gloss enamel suitable for interior and exterior use as a protective or decorative coating on steel and wood.
SECTION B:	COMPOSITION Alkyd Resin in white spirit
SECTION C:	PHYSICAL PROPERTIES Colour: White, Black, Colour Card colours Appearance: High Gloss Gloss: >80% @ 60° Viscosity: 70 - 75 Ku FC4 @ 25°C. S.G.: 1.00 - 1.05 Mass Solids: 21 - 26% Volume Solids: 14 - 19% Shelf Live: 12 Months Storage Conditions: Normal Pack Size: 1ℓ, 5ℓ, 20ℓ
SECTION D:	APPLICATION PROPERTIES Method: Brush, Roller, Airless Spray Average Dft: 40 microns (Recommended) Spreading Rate: 6 - 8m ² /ℓ Wet Film Thickness: 90 - 100 microns Number of coats: 2 - 3 as required Drying Time: Surface 5 - 7hrs, hard 24hrs max Overcoating Time: Between 24 - 72hrs Cleaning Solvent: Excelsior Turps Recommended systems: As a finishing and decorative coating on previously painted or new surface which have been well prepared or primed, for interior or exterior use.
SECTION E:	PRECAUTION Flash point: Below 24°C Toxicity: Normal when used in well ventilated areas
SECTION F:	SURFACE PREPARATIONS - All surfaces to be thoroughly clean, dry and free from grease, dirt or flaking paint. - All loosely adhering material and powder such as distemper or lime must be removed, one coat of BONDING LIQUID applied and allowed to dry (18 hours). - Metal surfaces must be primed with the appropriate primer. 3.1 GALVANISED IRON - Remove storage oil with GI Cleaner and prime with one coat of AQUA METALPRIME. 3.2 MILD STEEL TO BE PRIMED WITH: - AQUA METALPRIME water-based primer. - Alkyd based GP RED OXIDE PRIMER or ZP PRIMER (with anti-corrosive zinc-phosphate pigments). FRESH PLASTER: - Once plaster is completely dry. Apply one coat of either: Alkyd PLASTER PRIMER (low alkalinity) recommended for interior plaster.



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

Wise Buy Hi-Gloss Enamel.../continued

PLIOLITE PLASTER PRIMER (Goodyear France technology) for maximum priming benefits (High alkalinity) recommended for exterior plaster.

PREVIOUSLY PAINTED EMULSION (PVA/ACRYLIC SURFACES)

- Loose material must be removed with sandpaper.
- Powdery surfaces sealed with BONDING LIQUID.
- Dirt or grime to be removed with sugar soap.

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

- Sandpaper thoroughly.
- Apply one coat of UNIVERSAL UNDERCOAT and allow to dry 18hrs.

SECTION G:

NOTE

No guarantees are implied by the recommendations contained herein; since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.