

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

Wise Buy PVA

SECTION A:	DESCRIPTION An economical general purpose matt acrylic paint for interior and exterior surfaces (recommended interior) available in a white and a range of colour card colours. With limited washability.
SECTION B:	COMPOSITION Co-polymer emulsion
SECTION C:	PHYSICAL PROPERTIES Colour: White and as per colour card Appearance: Matt Gloss: < 15% @ 85° Viscosity: 90 - 105 Ku @ 25°C S.G.: 1.25 - 1.30 Mass Solids: 34 - 39% Volume Solids: 17 - 22% Shelf Life: 12 Months Storage Conditions: Normal Pack Size: 5l, 20l
SECTION D:	APPLICATION PROPERTIES Method: Brush, airless spray or roller Spreading Rate: 5 - 8m ² /l Number of coats: 2 Drying Time @ 25°C: Hard 4hrs (depending on moisture and humidity). Allow 14 days to cure before washing. Overcoating Time @ 25°C: 4hrs Thinning: Not Applicable Cleaning Solvent: Water Recommended systems: As described above
SECTION E:	PRECAUTION Flash point: Water-based Toxicity: see M.S.D.S.
SECTION F:	SURFACE PREPARATION - All surfaces to be thoroughly clean, dry and free from grease, dirt or flaking paint. - All loosely adhering material and powder such as distemper or lime must be removed, one coat of BONDING LIQUID applied and allowed to dry (18 hours). Metal surfaces must be primed with the appropriate primer. GALVANISED IRON Remove storage oil with GI CLEANER and prime with one coat of AQUA METALPRIME. MILD STEEL TO BE PRIMED WITH: - AQUA METALPRIME water-based primer. - Alkyd based GP RED OXIDE PRIMER or ZP PRIMER (with anti-corrosive zinc-phosphate pigments). FRESH PLASTER: Once plaster is completely dry. Apply one coat of either: - Excelsior AQUA-PLASTER PRIMER (water-based). or Excelsior PLIOLITE PLASTER PRIMER (Goodyear France technology) (solvent-based).

PRODUCT DATA SHEET

Reviewed 01/02/2016



YOU CAN'T BUY A BETTER PAINT FOR LESS!™

Wise Buy PVA.../continued

or Excelsior ALKALI RESISTANT PLASTER PRIMER (Solvent-based).

PREVIOUSLY PAINTED EMULSION (PVA/ACRYLIC SURFACES)

Loose material must be removed with sandpaper.

Powdery surfaces sealed with BONDING LIQUID.

Dirt or grime to be removed with sugar soap.

PREVIOUSLY PAINTED ENAMEL (Hi-gloss or Eggshell) SURFACES

Sandpaper thoroughly.

Apply one coat of UNIVERSAL UNDERCOAT and allow to dry 18 hours.

SECTION G:

NOTE

No guarantees are implied by the recommendations contained herein; since the data sheet is issued for information only. Method of application, surface cleanliness, conditions of use etc. are beyond our control.